



Product: BPM-Propylen - PP Regrind

Color: Colorful

Type: Regrind

Filtration: 6-8 mm Grain size



Parameter	Norm	Guideline	Unit
Density	EN ISO 55990	0,95	g/cm³
Melt flow index	EN ISO 1133	7,0	g/10 min.
E tensile modulus	EN ISO 527	1400	MPa
Charpy Impact strength 23°C	EN ISO 179	90	kJ/m²
Charpy notched bar impactstrength 23°C	EN ISO 179	6,0	kJ/m²
Tensile yield strength	EN ISO 527	26	MPa
Elongation at yield	EN ISO 527	>50	%

All informatin on this product data sheet are average values and are based on our current knowledge and experiences. They do not excuse the user of own examinations and experiments. A legally binding undertaking of certain qualities or the suitability for a specific application can not be derived from this data.

Applications :

PP is used as a casing material for small electrical appliances, moulded parts for household appliancesand for body parts (bumpers) and moulded parts in the interior of motor vehicles. In the construction sector, PP is used for pipes, hot water tanks and garden furniture.



Adress:

Best Plastic Management GmbH
Industriestraße 20-24
26219 Bösel
Germany

+49 (0) 44 94 / 15 55
+49 (0) 44 94 / 83 27

info@best-plastic.de
www.best-plastic.de

Documents:

Packaging:

Certification: