



Product: BPM-Propylen - PP Granulat nature

Color: Nature

Type: Granulat

Filtration: 150 my



Parameter	Norm	Guideline	Unit
Density	EN ISO 55990	0,91	g/cm ³
Melt flow index	EN ISO 1133	6,0	g/10 min.
E tensile modulus	EN ISO 527	>1100	MPa
Charpy Impact strength 23°C	EN ISO 179	90	kJ/m ²
Charpy notched bar impactstrength 23°C	EN ISO 179	>5,0	kJ/m ²
Tensile yield strength	EN ISO 527	25	MPa
Elongation at yield	EN ISO 527	>50	%

All informatin on this product data sheet are average values and are based on our current knowledge and experiences. They do not excuse the user of own examinations and experiments. A legally binding undertaking of certain qualities or the suitability for a specific application can not be derived from this data.

Applications :

PP is used as a casing material for small electrical appliances, moulded parts for household appliances and for body parts (bumpers) and moulded parts in the interior of motor vehicles. In the construction sector, PP is used for pipes, hot water tanks and garden furniture.



EuCertPlast

Adress:

Best Plastic Management GmbH
 Industriestraße 20-24
 26219 Bösel
 Germany

+49 (0) 44 94 / 15 55
 +49 (0) 44 94 / 83 27

info@best-plastic.de
 www.best-plastic.de

Documents:

Packaging:

Certification: