



Product: BPM-Styrol - PS Granulat

Color: Black, Anthracite, Colorful

Type: Granulat

Filtration: 150 my

Parameter	Norm	Guideline	Unit
Density	EN ISO 55990	1,05	g/cm ³
Melt flow index	EN ISO 1133	7,0	g/10 min.
E tensile modulus	EN ISO 527	2100	MPa
Charpy Impact strength 23°C	EN ISO 179	35	kJ/m ²
Charpy notched bar impactstrength 23°C	EN ISO 179	7,0	kJ/m ²
Tensile yield strength	EN ISO 527	25	MPa
Elongation at yield	EN ISO 527	1,5	%

All informatin on this product data sheet are average values and are based on our current knowledge and experiences. They do not excuse the user of own examinations and experiments. A legally binding undertaking of certain qualities or the suitability for a specific application can not be derived from this data.

Applications :

- Insulating films and plates for further processing, eg. B. by thermoforming, pipes and profiles
- Moldings and housings for radios, televisions, notebooks, telephones, computers, printers, power tools, optical devices, household and garden tools, garden furniture, hulls
- Drawing instruments, fluorescent screens, toys
- Interior panels for refrigerators and freezers
- In the automotive industry, among other things, as cladding elements, dashboards, ventilation systems, roof linings, battery cases, spoilers, radiator grills and hubcaps



Adress:

Best Plastic Management GmbH
 Industriestraße 20-24
 26219 Bösel
 Germany

+49 (0) 44 94 / 15 55
 +49 (0) 44 94 / 83 27

info@best-plastic.de
 www.best-plastic.de

Documents:

Packaging:

Certification: