

**Produkt:** BPM HIPS Regranulat A07

---

**Farbe:** Black, Grey 7047, Colorful, Anthracite 7015

---

**Type:** Granulat

---

**Filtrierung:** 150 my

---



Parameter	Norm	Guideline	Unit
Density	EN ISO 55990	1,05	g/cm <sup>3</sup>
Melt Flow index	EN ISO 1133	5,5	g/10 min.
E tensile modulus	EN ISO 527	1950	MPa
Charpy Impact strength 23 °C	EN ISO 179	35	kJ/m <sup>2</sup>
Charpy notched bar impact strength 23 °C	EN ISO 179	7	kJ/m <sup>2</sup>
Tensile yield strength	EN ISO 527	22,2	MPa
Elongation at yield	EN ISO 527	1,4	%
Tensile strength	EN ISO 527	18,3	MPa
Purity		99	%

All informatin on this product data sheet are average values and are based on our current knowledge and experiences. They do not excuse the user of own examinations and experiments. A legally binding undertaking of certain qualities or the suitability for a specific application can not be derived from this data.

**Documents:**

---

**Packaging:**

---

**Certification:**

---

### Anwendungen :

- + Packaging industry, trays, films, sheets
- + Film production (ABA process)
- + Garden industry, among other things, as trays and flower pots
- + Furniture industry for stands, interior cladding and handles
- + Insulating foils and panels for further processing for example through thermoforming, pipes and profiles
- + Technical applications including filter frames and picture frames
- + Technical compounds like housing



### Adresse:

Best Plastic Management GmbH  
Industriestraße 20-24  
26219 Bösel  
Germany

+49 (0) 44 94 / 15 55  
+49 (0) 44 94 / 83 27

info@best-plastic.de  
www.best-plastic.de

