

Produkt: BPM PS Regranulat A04

Farbe: Black, Grey 7047, Colorful, Anthracite 7015

Type: Granulat

Filtrierung: 150 my



Parameter	Norm	Guideline	Unit
Density	EN ISO 55990	1,05	g/cm ³
Melt Flow index	EN ISO 1133	5,5	g/10 min.
E tensile modulus	EN ISO 527	2100	MPa
Charpy Impact strength 23 °C	EN ISO 179	30	kJ/m ²
Charpy notched bar impact strength 23 °C	EN ISO 179	4	kJ/m ²
Tensile yield strength	EN ISO 527	16,7	MPa
Elongation at yield	EN ISO 527	1,8	%
Tensile strength	EN ISO 527	17,3	MPa
Purity		99	%

All informatin on this product data sheet are average values and are based on our current knowledge and experiences. They do not excuse the user of own examinations and experiments. A legally binding undertaking of certain qualities or the suitability for a specific application can not be derived from this data.

Documents:

Packaging:

Certification:

Anwendungen :

- + Packaging industry, trays, films, sheets
- + Film production (ABA process)
- + Garden industry, among other things, as trays and flower pots
- + Furniture industry for stands, interior cladding and handles
- + Insulating foils and panels for further processing for example through thermoforming, pipes and profiles
- + Technical applications including filter frames and picture frames
- + Technical compounds like housing



Adresse:

Best Plastic Management GmbH
Industriestraße 20-24
26219 Bösel
Germany

+49 (0) 44 94 / 15 55
+49 (0) 44 94 / 83 27

info@best-plastic.de
www.best-plastic.de

